

PRECISION PAPER COATINGS PTY LTD
25 MIOWERA ROAD, VILLAWOOD NSW 2163
AUSTRALIA
TEL: 612 9780 9000
FAX: 612 9728 9966
Email: ross@ppcpl.com.au
WEB: www.ppcpl.com.au



APPLICATION PROCEDURE FOR TAPE

PRODUCT: PPC No. 493 REINFORCED ALUMINIUM FOIL TAPE

SITE: CSR Edmunds Central Coast NSW

DATE: 23/2/2010

TYPE OF APPLICATION: Simulation of underslab insulation as per RIVERLINK Project in Ipswich Qld. The tape is being used to join foil faced insulation.

METHOD:

- A clean cloth is used to wipe the area along the joins where the tape is to be applied.
- Where the surface area is contaminated with oily substance, mineral turpentine is applied to the cloth, the area wiped clean and allowed to dry.
- Remove the silicone liner paper from the tape and align equally over the join.
- A plastic "squeegee" is then used to progressively apply and rub down the tape, importantly following the contours of the foil faced insulation.
- Sufficient pressure is used with the "squeegee" so there are no air bubbles underneath the tape and that 100% contact is achieved.

PPC PERSONNEL: ROSS OAKMAN
BRIAN PEARSON

Ross Oakman
Sales & Marketing Director