

Acoustigard® Partition Rolls

Refer to product table below for applicable product codes covered by this document

Issue **H**

Product Type & Application

Acoustigard® Partition Rolls are non-combustible Glasswool rolls for thermal and acoustic insulation in internal or external partitions and walls. They are also suitable for roof or ceiling use.

Compliance with the NCC

For use in Australia, when correctly specified and installed, this product:

NCC 2022

- **Thermal** - Complies with NCC 2022 Volume 1 J4D3(1) and ABCB Housing Provisions Standard 2022 13.2.2(1). This product meets the requirements of the NCC through compliance with AS/NZS 4859.1.
- **Acoustics** - Reported thickness and density provide details for compliance with Deemed-To-Satisfy sound insulation construction in NCC 2022 Volume 1 Specification 28 and ABCB Housing Provisions Standard 2022 Part 10.7.
- **Fire Hazard Properties** - Meets the requirements of the NCC 2022 Volume 1, S7C7 for insulation materials. When assessed to AS/NZS 1530.3 this product does not exceed the 'Spread of Flame' or 'Smoke Developed' indices of Table S7C7.
- **Non-Combustibility** - Meets the non-combustible requirements of NCC 2022 Volume 1 C2D10(1) when assessed in accordance with AS 1530.1.

NCC 2019

- **Thermal** - Complies with NCC 2019 Volume 1 Amend. 1 Section J1.2(a), NCC 2019 Volume 2 Amend. 1 Section 3.12.1.1(a), and all state-prescribed variations. The product meets the requirements of the NCC through compliance with AS/NZS 4859.1.
- **Acoustics** - Reported thickness and density provide details for compliance with Deemed-To-Satisfy sound insulation construction in NCC 2019 Volume 1 Amend. 1 Specification F5.2 and Acceptable Construction Practice in NCC 2019 Volume 2 Amend. 1 Tables 3.8.6.1a-3.8.6.1d.
- **Fire Hazard Properties** - Meets the requirements of the NCC 2019 Volume 1 Amend. 1, Specification C1.10 Clause 7 for insulation materials. When assessed to AS/NZS 1530.3 this product does not exceed the 'Spread of Flame' or 'Smoke Developed' indices of Specification C1.10 Clause 7.
- **Non-Combustibility** - Meets the non-combustible requirements of NCC 2019 Volume 1 Amend. 1 C1.9(a) when assessed in accordance with AS 1530.1.

Limitations of Use

- **IMPORTANT:** Do Not Modify This Product: Compliance with the evidence of suitability data referenced in this document is only achieved by the product or configuration listed in this PTS.
- **IMPORTANT:** Acoustigard 24 and Acoustigard 32 are high-density products that will not compress during installation and must be installed in a cavity of the correct size, with no obstructions. If installed in a cavity smaller than the product's nominal thickness, there is a risk of deformation or detachment of rigid wall lining materials.
- This product is not suitable for use as an exposed internal wall or ceiling lining in applications which require a Group Number in accordance with AS ISO 9705 and AS 5637.1 (NCC 2019 Volume 1 Amend. 1, Specification C1.10 Clause 4, NCC 2022 Volume 1 S7C4).
- Unfaced Glasswool is not a water or vapour barrier and is not suitable for water or vapour control.
- Check the plasterboard, ceiling tile or ceiling grid manufacturer's weight limitations prior to increasing the recommended R-Values or densities to ensure the structure can support the additional weight of the insulation batts.
- Consult AS 3959 to determine the installation conditions when using unfaced rolls in roofs of buildings in bushfire-zoned areas.
- Maximum service temperature is 300°C for Glasswool.

Conditions of Storage, Use & Maintenance

Store in the original packaging in a cool, dry area, away from foodstuffs. Ensure packages are adequately labelled, protected from physical damage, and sealed when not in use. Avoid packaging being stored under UV light (direct sunlight) for long periods.

Refer to the product SUIS/MSDS at Bradfordinsulation.com.au for more information.

Acoustigard® Partition Rolls

Specific Design or Installation Instructions

- Isolate power before installation.
- **IMPORTANT:** Acoustigard 24 and Acoustigard 32 are high-density products that will not compress during installation and must be installed in a cavity of the correct size, with no obstructions. If installed in a cavity smaller than the product's nominal thickness, there is a risk of deformation or detachment of rigid wall lining materials.
- **Caution:** Electrical cables and equipment partially or completely surrounded with bulk thermal insulation may overheat and fail. In new build construction with electrical wiring in accordance with AS/NZS 3000: 2018 or later, wiring may be partially or completely surrounded for up to 400mm. If more than 400mm is surrounded, or for wiring pre AS/NZS 3000:2018, seek advice from a licenced electrician. Refer to legislation and referenced standards for full details or seek advice from an electrician if in doubt.
- Suitable for applications that specify non-combustible bulk insulation products - not suitable for exposed internal wall and ceiling lining applications that require a Group Number.
- Suitable for applications where the product is protected from direct UV light, water and wind pressure during and after installation.
- Insulation should be installed so that it forms a continuous layer and abuts or overlaps adjoining insulation other than at supporting frame members such as columns, studs, noggings, joists, furring channels and the like where the insulation must butt against the member.
- Compensate for gaps as specified by the NCC 2019 Volume 2 Amend. 1, 3.12.1.2(e) and Table 3.12.1.1h, ABCB Housing Provisions Standard 2022 13.2.3(5) and Table 13.2.3w. It should be installed at nominal thickness, except where it crosses structures, services and fittings.
- Ceiling perimeter batts may be required to achieve compliance depending upon roof and exterior wall design.

Supplementary information - Additional installation guidance for this product can be found in AS 3999.

Evidence of Suitability

- Testing to AS/NZS 4859.1 across the following reports-
 - CSR Lab Report R-20033.
 - CSR Lab Report R-20034.
 - CSR Lab Report R-20035.
 - CSR Lab Report R-20036.
 - CSR Lab Report R-20037.
 - CSR Lab Report R-20038.
 - CSR Lab Report R-20039.
 - CSR Lab Report R-20040.
 - CSR Lab Report R-20041.
 - CSR Lab Report R-20044.
 - CSR Lab Report R-20045.
 - CSR Lab Report R-20046.
 - CSR Lab Report R-20047.
 - CSR Lab Report R-20048.
 - CSR Lab Report R-20049.
 - CSR Lab Report R-20070.
 - CSR NATA Lab Report NR-23105.
 - AWTA NATA Lab Report 23-000640.
 - AWTA NATA Lab Report 23-001631.
 - AWTA NATA Lab Report 23-001633.
- Professional Assessment, AS/NZS 1530.3 - Warringtonfire Assessment FAS200045.
- Testing and Professional Assessment, AS 1530.1 –
 - CSR Lab NATA Report NR-16001.
 - CSR Lab NATA Report NR-16007.
 - CSR Lab NATA Report NR-16008.
 - CSR Lab NATA Report NR-17002.
 - CSR Lab NATA Report NR-17005.
 - CSR Lab NATA Report NR-17006.
 - CSR Lab NATA Report NR-17007.
 - CSIRO Assessment FCO-2812.

Acoustigard® Partition Rolls

Applicable Product Codes

R-VALUE (m ² K/W)	DENSITY (kg/m ³)	THICKNESS (mm)	LENGTH (m)	WIDTH (mm)	ROLLS PER PACK	COVERAGE PER PACK (m ²)	PRODUCT CODE
#R1.0	11	50	16.2	450	3	21.9	119466#
#R1.0	11	50	16.2	600	2	19.4	119467#
R1.7	11	75	13.5	450	3	18.2	119468^
R1.7	11	75	13.5	600	2	16.2	119469^
R2.5	11	110	8.1	600	2	9.7	119511
R3.5	11	165	5.4	600	2	6.5	119470^
R1.2	14	50	16.2	450	3	21.9	119521^
R1.2	14	50	16.2	600	2	19.4	119522^
R1.8	14	75	13.5	450	3	18.2	119523^
R1.8	14	75	13.5	600	2	16.2	119524^
R2.2	14	90	10.8	450	3	14.6	73776^
R2.2	14	90	10.8	600	2	13.0	87731^
R2.4	14	100	10.8	450	3	14.6	119527
R2.4	14	100	10.8	600	2	13.0	119526
#R0.6	18	25	21.6	600	2	25.9	119373#
#R1.3	18	50	10.8	450	3	14.6	119375#
#R1.3	18	50	10.8	600	2	13.0	119376#
#R2.0	18	75	8.1	450	3	10.9	119377#
#R2.0	18	75	8.1	600	2	9.7	119379#
#R2.5	18	100	8.1	450	3	10.9	456770#
#R2.5	18	100	8.1	600	2	9.7	456815#
#R2.4	20	90	5.4	450	3	7.3	119462#
#R2.4	20	90	5.4	600	2	6.5	119463#
R0.65	24	25	16.2	450	3	21.9	479731^
R0.65	24	25	16.2	600	2	19.4	479730^
R1.4	24	50	10.8	450	3	14.6	119529^
R1.4	24	50	10.8	600	2	13.0	119528^
R2.1	24	75	8.1	450	3	10.9	119530^
R2.1	24	75	8.1	600	2	9.7	119551^
R2.5	24	90	5.4	450	3	7.3	456978^
R2.5	24	90	5.4	600	2	6.5	457190^
R0.7	32	25	16.2	450	3	21.9	456817^
R0.7	32	25	16.2	600	2	19.4	456859^
R1.5	32	50	8.1	450	3	10.9	119587^
R1.5	32	50	8.1	600	2	9.7	119588^
R2.2	32	75	5.4	450	3	7.3	119589^
R2.2	32	75	5.4	600	2	6.5	119631^
R2.7	32	90	5.4	450	3	7.3	162853^
R2.7	32	90	5.4	600	2	6.5	162852^

Product discontinued 31st July 2022.

^ AS/NZS 1530.3 Test Report available.

Acoustigard® Partition Rolls

Additional Product Data

Maximum Service Temperature		300°C (suitable where a long term surface operating temperature $\geq 90^{\circ}\text{C}$ is required for insulation around heat generating equipment.)
Fire Hazard Properties	When assessed in accordance with AS/NZS 1530.3	<ul style="list-style-type: none"> • Ignitability: 0 • Spread of Flame: 0 • Heat Evolved: 0 • Smoke Developed: 1
Non-Combustibility	When assessed to AS 1530.1	Non - Combustible
Sample Specification	The insulation material shall be Bradford Acoustigard Partition Rolls having a material R-Value; R_m(specify R-Value) @ XXmm....(specify thickness) having a nominal density $YY\text{kg/m}^3$(specify density), and shall be deemed non-combustible when tested to AS 1530.1. For installation specifications refer to the relevant Bradford Product Selector.	

Acoustic Performance

Sound absorption results tested in accordance with AS/ISO 354-2006. NRC rated in using ASTM C423-90A, and weighted sound absorption coefficient α_w as per AS/ISO 11654-1997. Flow Resistivity tested in accordance with ASTM C522 -

Density (kg/m ³)	Thickness (mm)	Sound Absorption Coefficient (α_s)	Frequency (Hz)							NRC	Flow Resistivity (mks rayl/m)	α_w
			125	250	500	1000	2000	4000	5000			
11	75		0.26	0.63	0.97	0.87	0.92	0.97	0.95	0.85	3180	0.90
14	75		0.26	0.71	1.03	1.00	0.95	0.99	0.97	0.90	5840	0.95
18	50		0.22	0.58	0.93	1.04	1.00	1.04	1.10	0.90	8490	0.85
24	50		0.24	0.64	1.00	1.06	1.01	1.05	1.05	0.95	11310	0.90
32	50		0.24	0.64	1.11	1.08	1.06	1.02	1.04	0.95		0.95
32	75		0.35	1.08	1.19	1.05	1.02	1.00	1.01	1.10	18440	1.00

Other Accreditation



FBS-1 Glasswool - The fibre component of these products is listed by Safe Work Australia as Man-made Vitreous Fibre (Glasswool) of low bio persistence as specified under Note Q in the Australian Hazardous Substances Information System and in the Australian Approved Criteria documentation. In accordance with EU ATP 31 (2009) these fibres are not classified as an irritant, or as carcinogenic. Refer to the product SUIS/MSDS at Bradfordinsulation.com.au for more information.



National Asthma Council Sensitive Choice