

Multitel® BAL 12.5-40 Blanket

Refer to product table below for applicable product codes covered by this document

Issue **A**

Product Type & Application

Multitel® BAL 12.5-40 is a low density, non-combustible Glasswool blanket. Multitel® BAL 12.5-40 is primarily intended to seal against ember ingress to metal roofs in bushfire prone regions classified as Bushfire Attack Level (BAL) 12.5-40. For the properties of Multitel HVAC Blankets refer to their separate Product Technical Statement.

Compliance with the NCC

For use in Australia, when correctly specified and installed, this product:

- **Fire Hazard Properties** - Meets the requirements of the NCC 2019 Volume 1, Specification C1.10 Clause 7 for insulation materials. When tested to AS/NZS 1530.3 this product does not exceed the 'Spread of Flame' or 'Smoke Developed' indices of Specification C1.10 Clause 7.
- **Non-Combustibility** - Meets the requirements of NCC Vol.1 C1.9(a), as it is non-combustible when tested to AS 1530.1.

Evidence of Suitability

- Testing and Professional Assessment, AS/NZS 1530.3 -
 - CSIRO Assessment FCO-2805.
- Testing and Professional Assessment, AS 1530.1 –
 - CSIRO Assessment FCO-2812.

Conditions of Storage, Use & Maintenance

- Store in the original packaging in a cool, dry area, away from foodstuffs. Ensure packages are adequately labelled, protected from physical damage, and sealed when not in use. Avoid packaging being stored under UV light (direct sunlight) for long periods. Store in the original packaging in a cool, dry area, removed from UV light (direct sunlight).

Refer to the product SUI/MSDS at Bradfordinsulation.com.au for more information.

Specific Design or Installation Instructions

- Isolate power before installation.
- **Caution:** Electrical cables and equipment partially or completely surrounded with bulk thermal insulation may overheat and fail. In new build construction with electrical wiring in accordance with AS/NZS 3000, 2018 version or later, wiring may be partially or completely surrounded for up to 400mm. If more than 400mm is surrounded, or for wiring pre AS/NZS 3000, 2018 version, seek advice from a licenced electrician. Refer to legislation and referenced standards for full details.
- Insulation should be compressed into position to fully seal openings. Refer to the Bradford Bushfire Roofing Systems Design Guide.
- Install in accordance with the requirements of AS 3959.
- Do not allow insulation to get wet after installation.

For general installation guidance refer to the **Bradford Bushfire Roofing Systems Design Guide**, or product information on Bradfordinsulation.com.au

Supplementary information - Additional installation guidance for this product can be found in AS3999.

Limitations of Use

- Not intended to seal tiled roofs in BAL classified areas.
- Not suitable for use in BAL-FZ.
- Unfaced Glasswool is not a water or vapour barrier and is not suitable for water or vapour control.
- Not to be used for external concrete slab insulation.
- Maximum service temperature is 300°C for Glasswool.

Multitel® BAL 12.5-40 Blanket

Applicable Product Codes

THICKNESS (mm)	NOMINAL LENGTH (m)	NOMINAL WIDTH (mm)	LINEAR METERS PER PACK	PRODUCT CODE
25	20	300	80	100061

Additional Product Data

Maximum Service Temperature		300°C
Fire Hazard Properties	When tested in accordance with AS/NZS 1530.3	• Ignitability: 0 • Spread of flame: 0 • Heat Evolved: 0 • Smoke Developed: 0-1
Non-Combustibility	When tested to AS 1530.1	Non - Combustible

Other Accreditation



FBS-1 Glasswool - The fibre component of these products is listed by Safe Work Australia as Man-made Vitreous Fibre (Glasswool) of low bio persistence as specified under Note Q in the Australian Hazardous Substances Information System and in the Australian Approved Criteria documentation. In accordance with EU ATP 31 (2009) these fibres are not classified as an irritant, or as carcinogenic. Refer to the product SUI/MSDS at Bradfordinsulation.com.au for more information.