

# Ultratel HVAC Board

Refer to product table below for applicable product codes covered by this document

Issue **E**

## Product Type & Application

Ultratel is a high density Glasswool board. It provides thermal resistance, acoustic properties; and is available with or without facing materials. Ultratel is primarily intended for use as insulation for HVAC silencers and internal duct lining for commercial applications.

## Compliance with the NCC

For use in Australia, when correctly specified and installed, this product provides the following compliance:

### NCC 2022

- **Thermal** - Complies with NCC 2022 Volume 1 J4D3(1) and ABCB Housing Provisions Standard 2022 13.2.2(1). This product meets the requirements of the NCC through compliance with AS/NZS 4859.1.
- **Fire Hazard Properties** - Meets the requirements of the NCC 2022 Volume 1 S7C5 for Air Handling Ductwork and S7C7 for insulation materials. When assessed to AS/NZS 1530.3 this product does not exceed the 'Spread of Flame' or 'Smoke Developed' indices of S7C5 or Table S7C7.

### NCC 2019

- **Thermal** - Complies with NCC 2019 Volume 1 Amend. 1 Section J1.2(a), NCC 2019 Volume 2 Amend. 1 Section 3.12.1.1(a), and all state-prescribed variations. The product meets the requirements of the NCC through compliance with AS/NZS 4859.1.
- **Fire Hazard Properties** - Meets the requirements of the NCC 2019 Volume 1 Amend. 1 Specification C1.10 Clause 5 for Air Handling Ductwork and Clause 7 for insulation materials. When assessed to AS/NZS 1530.3 this product does not exceed the 'Spread of Flame' or 'Smoke Developed' indices of Specification C1.10 Clause 5 or 7.

## Conditions of Storage, Use & Maintenance

- Store in the original packaging in a cool, dry area, away from foodstuffs. Ensure packages are adequately labelled, protected from physical damage, and sealed when not in use. Avoid packaging being stored under UV light (direct sunlight) for long periods. Store in the original packaging in a cool, dry area, removed from UV light (direct sunlight).
- Do not pressure clean or use mineral based cleaners on the facing product.

Refer to the product SUI/MSDS at [Bradfordinsulation.com.au](http://Bradfordinsulation.com.au) for more information.

## Limitations of Use

- **IMPORTANT:** Compliance with the evidence of suitability data referenced in this document is only achieved when this product is produced at a CSR approved facility, in accordance with CSR specifications and approved materials.
- **IMPORTANT:** Do Not Modify This Product: Compliance with the evidence of suitability data referenced in this document is only achieved by the product or configuration listed in this PTS.
- This material is not classified as non-combustible in accordance with AS1530.1 and is not suitable for use where non-combustible material is required.
- This product does not meet the non-combustibility or fusion temperature requirements of AS 1668.1 – The use of ventilation and air conditioning in buildings, 2.3.2.
- This product is not suitable for use as an exposed internal wall or ceiling lining in applications which require a Group Number in accordance with AS ISO 9705 and AS 5637.1 (NCC 2019 Volume 1 Amend. 1, Specification C1.10 Clause 4, NCC 2022 Volume 1 S7C4).
- Unfaced Glasswool is not a water or vapour barrier and is not suitable for water or vapour control.
- Maximum service temperature is 300°C for unfaced Glasswool, 70°C for faced Glasswool.
- The foil facing product should not come into contact with wet concrete, or alkaline materials.

## Evidence of Suitability

- Testing to AS/NZS 4859.1 across the following reports apply to the unfaced board -
  - CSR Lab Report R-20061.
  - CSR Lab Report R-20062.
  - CSR Lab Report R-20063.
  - CSR Lab Report R-20064.
- Professional Assessment, AS/NZS 1530.3 -
  - Warringtonfire Assessment FAS200045.
- Professional Assessment, UL 181.11 -
  - Warringtonfire Assessment FAS200051.

## Ultratel HVAC Board

### Specific Design or Installation Instructions

- Isolate power before installation.
- **WARNING:** This product contains aluminium foil which conducts electricity. To avoid electrocution, care should be taken to ensure that this product or conductive fasteners used to secure this product, do not come into contact or close proximity with electrical wiring during installation or use.
- **Caution:** Electrical cables and equipment partially or completely surrounded with bulk thermal insulation may overheat and fail.
- Suitable for applications where the product is protected from direct UV light, water and wind pressure during and after installation.
- Stated thermal performance is based on the insulation blanket or board only - reflective R-values are construction-dependent upon the adjacent airgap and must be determined in accordance with AS/NZS 4859.2.
- Refer to AS 4254.1 or AS 4254.2 for installation requirements for air handling ductwork.

For general installation guidance refer to the product information on [Bradfordinsulation.com.au](http://Bradfordinsulation.com.au)

### Applicable Product Codes

R-VALUE (m <sup>2</sup> K/W)	THICKNESS (mm)	NOMINAL LENGTH (m)	NOMINAL WIDTH (mm)	PIECES PER PACK	m <sup>2</sup> PER PACK	PRODUCT CODE
<b>PLAIN</b>						
R0.75	25	2.4	1200	6	17.3	15324
R1.5	50	2.4	1200	3	8.6	15278 <sup>^</sup>
R2.3	75	2.4	1200	2	5.7	68919
R3.0	100	2.4	1200	2	5.7	41906
<b>BLACK MATT FACING (BMF)</b>						
R0.75	25	2.4	1200	6	17.3	15277
R1.5	50	2.4	1200	3	8.6	15298 <sup>^</sup>
<b>ACOUSTITUFF® FACING</b>						
R0.75	25	2.4	1200	6	17.3	17586
R1.5	50	2.4	1200	3	8.6	63281 <sup>^</sup>
<b>HEAVY DUTY PERFORATED FACING (HDP)</b>						
R0.75	25	2.4	1200	6	17.3	15267
R1.5	50	2.4	1200	3	8.6	15286 <sup>^</sup>
R2.3	75	2.4	1200	2	5.7	77951
R2.3	75	2.4	1500	2	7.2	122496
R3.0	100	2.4	1200	2	5.7	28865

R-values are determined in accordance with AS/NZS 4859.1. The contribution of the reflective air-gap is construction dependant and excluded from the declared R-value. The duty classification of the facing material does not influence the R-value.

<sup>^</sup> AS/NZS 1530.3 Test Report available.

## Ultratel HVAC Board

### Additional Product Data

<b>Maximum Service Temperature</b>		<ul style="list-style-type: none"> <li>• 300°C for Unfaced Glasswool</li> <li>• 70°C for Faced Glasswool</li> </ul>
<b>Volatile Organic Compound (VOC) and Formaldehyde Emissions</b>	When tested in accordance with ASTM D5116	<ul style="list-style-type: none"> <li>• VOC 0.5 mg/m<sup>2</sup>/hr</li> <li>• Formaldehyde 0.2 mg/m<sup>2</sup>/h</li> </ul>
<b>Fire Hazard Properties</b>	When assessed in accordance with AS/NZS 1530.3	<p><b>Unfaced Board:</b></p> <ul style="list-style-type: none"> <li>• Ignitability: 0 • Spread of flame: 0</li> <li>• Heat Evolved: 0 • Smoke Developed: 1</li> </ul> <p><b>BMF Faced Board:</b></p> <ul style="list-style-type: none"> <li>• Ignitability: 18 • Spread of flame: 0</li> <li>• Heat Evolved: 0 • Smoke Developed: 3</li> </ul> <p><b>Acoustituff® Faced Board:</b></p> <ul style="list-style-type: none"> <li>• Ignitability: 0 • Spread of flame: 0</li> <li>• Heat Evolved: 0 • Smoke Developed: 1</li> </ul> <p><b>Heavy Duty Perforated Faced Board:</b></p> <ul style="list-style-type: none"> <li>• Ignitability: 0 • Spread of flame: 0</li> <li>• Heat Evolved: 0 • Smoke Developed: 3</li> </ul>
<b>UL-181 Burning Test</b>	Insulation 25-100mm thick was assessed in a representative duct section to UL-181's Burning Test, as an indication of how it will perform when the assembled duct undergoes the test. AS 4254.1 and AS 4254.2 require the full duct assembly to be tested to UL 181. (NCC 2019 Volume 1 Amend. 1, Specification C1.10 Clause 5, NCC 2022 Volume 1 S7C5). Insulation satisfies criteria as an indicative test only – specific testing of the final assembly is necessary for the duct to meet Australian Standard requirements.	

### Acoustic Performance

Sound absorption results tested in accordance with AS/ISO 354-2006 and NRC rated using ASTM C423-90A, Flow Resistivity tested in accordance with ASTM C522-87.

Product	Thickness (mm)	Practical Sound Absorption Coefficient ( $\alpha_p$ )	Frequency (Hz)						NRC	Flow Resistivity (Rayl/m)	$\alpha_w$
			125	250	500	1000	2000	4000			
Ultratel with Acoustituff Facing	50mm		0.3	0.75	1.0	0.9	0.7	0.45	0.85		0.65 (LM)
Ultratel with HD Perforated Facing	50mm		0.2	0.7	1.0	1.0	1.0	1.0	1.05	37500	1.0
	75mm		0.4	1.0	1.0	1.0	1.0	0.95	1.10		1.0

The practical sound absorption coefficient is determined as per AS/ISO 11654-1997.  
The weighted sound absorption coefficient is determined as per AS/ISO 11654-1997.

### Other Accreditation



**FBS-1 Glasswool** - The fibre component of these products is listed by Safe Work Australia as Man-made Vitreous Fibre (Glasswool) of low bio persistence as specified under Note Q in the Australian Hazardous Substances Information System and in the Australian Approved Criteria documentation. In accordance with EU ATP 31 (2009) these fibres are not classified as an irritant, or as carcinogenic.  
**Refer to the product SUIS/MSDS at [Bradfordinsulation.com.au](http://Bradfordinsulation.com.au) for more information.**